

Product Data Sheet TIC 6050 Butyl Cryogenic Adhesive/Coating

Description

TIC 6050 Butyl Cryogenic Adhesive/Coating is two parts black elastomeric adhesive/coating designed for use in cryogenic and specific chemical resistance applications. It is suitable for application to polyurethane foam, cellular glass and fibrous glass insulations in conjunction with aluminum, steel, wood and masonry construction materials.

TIC 6050 Butyl Cryogenic Adhesive/Coating has excellent resistance of moisture, water vapour and other gases. It also has good resistance to most oils, mild solvents, inorganic acids, inorganic bases and salt solutions.

TIC 6050 Butyl Cryogenic Adhesive/Coating is suitable for bonding and sealing lap joints in plywood and metal, and for adhering glass cloth to itself and other surfaces. It can function both as a vapour barrier and as adhesive in very low temperature applications where a water vapour tight insulation system is required. It is an excellent vapour stop material.

TIC 6050 Butyl Cryogenic Adhesive/Coating contains no lead, asbestos, mercury or mercury compounds.

Properties

Property	Specification	Test method
Color	Black (mixed)	TSTM-01
Application	Brush, airless spray or roller	TSTM-06
Density	Mixed (A&B) - 1.15 ± 0.05 Kg/ℓ	ASTM D 1475
Volume non-volatile	65 ± 1 % (mixed)	ASTM D 1644
Weight non-volatile	73 ± 1 % (mixed)	ASTM D 1644
Coverage	1.42 Kg/m ² (1.23 ℓ/m ²) Dried film thickness: 0.8 mm	TSTM-07
Mixing ratio	Weight - part A : part B = 1 : 1 Volume - part A : part B = 1 : 1	TSTM-16
Bonding time	40 ~ 80 minutes	TSTM-17
Drying time	Set to touch: 12 hours Dry through: 48 hours Full curing time: 2 weeks	ASTM D 1640
Pot life	6 ~ 9 hours (25±2°C, 50±2% RH)	TSTM-09
Service temperature limits	(Temperature at coated surface) -196 °C ~ 121 °C (-321 °F ~ 250 °F)	TSTM-04
Water vapour permeance	≤ 0.013 perms (DFT 0.64 mm)	ASTM E 96
Wet flammability	≥ 44 °C (111 °F)	ASTM D 93
Tensile strength	≥ 300 psi (207 N/cm ²)	ASTM D 412

Limitations

Store and apply between 4 °C (40 °F) and 38 °C (100 °F).

Always test plastic materials for compatibility when using a solvent base product.

Make certain this product is completely dry and the area free from solvent odor if food is involved.

Not recommend for application between two impermeable surfaces or as an exposed finished coating.

Application

Material Preparation

Mixing instructions: Add TIC 6050 Butyl Cryogenic Adhesive/Coating part B into part A and mix thoroughly for about 5 minutes, using an air driven mechanical stirrer. Do not whip air into the product.

Application

Apply only to clean, dry surfaces. New concrete surfaces must be at least 4 weeks old.

When used as a vapor barrier adhesive, apply at the rate of 1 gal/100 sq.ft (0.41 ℓ/m²) and allow curing for 24 hours. Apply a second coat at 2 gal/100 sq.ft (0.81 ℓ /m²) and embed the insulation into the adhesive after 40 to 80 minutes open time, but before it skins over, making certain complete contact is made. When used as a vapor barrier and/or vapor stop, TIC 6050 Butyl Cryogenic Adhesive/Coating may be applied up to 2 gal/100 sq.ft (0.81 ℓ/m²) on vertical surfaces (21 mils/0.53 mm dry thickness).

Clean-up

Use solvents such as chlorinated solvent (non-flammable) or mineral spirits (flammable) for cleaning tools and equipment.

Completely clean all equipments before pot life expires, and the adhesive sets up. Dried TIC 6050 Butyl Cryogenic Adhesive/Coating is extremely difficult to remove.

Note

Important: We make no other warranties and expressly disclaim any warranties of merchantability or fitness for a particular purpose. If a product fails to meet this limited warranty, purchaser's sole and exclusive remedy is replacement of the product or, at our option, refund of the purchase price. Our acceptance of any orders for the product is expressly conditional upon purchaser's assent to the terms on the applicable invoice.

Adequate Tests: The information contained herein we believe is correct to the best of our knowledge and tests. The recommendations and suggestions herein are made without guarantee or representation as to results. We recommend that adequate tests be perform by you to determine if this product meets all of your requirements. The warranted shelf life of our products is twelve months from date of shipment to the original purchaser.

TIC CORPORATION

Headquarter & Factory: 106, 5sandan-2ro, Seongnam-myeon, Dongnam-gu, Cheonan-si, Chungcheongnam-do Province, Republic of Korea Tel +82 41 558 4252(Rep), Fax +82 41 558 9360, e-mail tic@tickorea.com

www.tickorea.com

Rev 3.1