

Description

TIC 8020 Vapour Barrier Sealant is a fire-resistive, fibrated water based, indoor/outdoor vapour barrier sealant for low, medium and high velocity heating and air conditioning ducts. It performs as a tough and flexible adhesive and sealant, forming a durable seal against air leakage when used with or without reinforcing tape or membrane. Mechanical fasteners of the type and number normally used for duct assemblies are required to provide rigidity to the duct system.

TIC 8020 Vapour Barrier Sealant has excellent weather resistance, low water vapour permeance and good water resistance, allowing it to be used outdoors and in high humidity environments. It is U.V. resistant. When dry, it may be painted with good quality water base paint.

TIC 8020 Vapour Barrier Sealant may be pressure tested within 24 hours dry time above 21 °C (70 °F). It quickly forms a strong bond to galvanized, aluminum or mild steel metal ducts. It has a mild odor when wet.

TIC 8020 Vapour Barrier Sealant contains no asbestos, lead, mercury, or mercury compounds.

Properties

Property	Specification	Test method
Color	Light gray	TSTM-01
Application	Brush, trowel, caulking gun, or power extrusion	TSTM-06
Density	1.38 ± 0.05 Kg/ℓ(11.5 lbs/gal)	ASTM D 1475
Volume non-volatile	58 ± 1 %	ASTM D 1644
Weight non-volatile	71 ± 1 %	ASTM D 1644
Coverage	Brush/Trowel 1.90 Kg/m ² (1.38 ℓ/m ²) Dried film thickness: 0.8 mm Caulking gun (310 ml tube) 3.2 mm bead:38 m/6.4mm bead:9 m	TSTM-07
Drying time	Set to touch: 1 hour Dry through: 24 hours	ASTM D 1640
Service temperature limits	(Temperature at coated surface) -7 °C ~ 93 °C (20 °F ~ 200 °F)	TSTM-04
Water vapour permeance	≤ 0.45 perms (DFT 0.9 mm)	ASTM E 96
Wet flammability	≥ 100 °C (212 °F),No flash to boiling	ASTM D 3278
Surface burning characteristics	Classification: CLASS A Flame spread: 5 (0~25) Smoke developed: 0 (0~450) Surface: Applied over fiber reinforced cement board at a coverage rate of 25 sq. ft/gal (4.6 m ² /ℓ)	ASTM E 84

Limitations

Store and apply between 4 °C (40 °F) and 38 °C (100 °F), protect from freezing until dry.

To resist rain washoff, allow at least 24 hours drying time above 4 °C (40 °F) with a relative humidity of 50 %. Higher humidity or lower temperatures may delay drying.

Always test foil and paper facings for acceptable adhesion.

Outdoor horizontal surfaces must always drain completely. At pitch of at least 1/2 inch per foot (4 cm/m) is required.

If used between impermeable surfaces, drying time will be extended.

Application

Material Preparation

DO NOT THIN. Apply only to clean, oil-free dry surfaces. Keep container closed when not in use.

Application

1. Brush/Trowel - Uniformly coat the TIC 8020 Vapour Barrier Sealant over the joint, at total coverage rate to be 0.6 ~ 1.2 m²/ℓ (wet film thickness: 1.6 ~ 0.8 mm). Allow the completed joint to dry at least 24 hours above 21 °C (70 °F) before pressure testing. High humidities (over 70%) and/or cooler temperature may retard drying.

Apply a continuous film of TIC 8020 Vapour Barrier Sealant over all areas of the indoor or outdoor duct system where air leakage may occur. A brush may be used to work the sealant into joints and remove excess. On spiral ducts apply a coat TIC 8020 Vapour Barrier Sealant to the male end of the coupling prior to fitting the straight run of spiral duct over it. Brush excess TIC 8020 Vapour Barrier Sealant over the joint to complete the seal. Screw holes and flanges should also be sealed with a coat of TIC 8020 Vapour Barrier Sealant. It may be applied to the inside or the outside of the duct.

2. Power extrusion - TIC 8020 Vapour Barrier Sealant may be applied using a wide variety of power (pressure) extrusion equipment suitable for use with water base sealants. It is a soft buttery gel with a typical viscosity range of 250,000 - 270,000 cps. Corrosion resistant pumps and fittings are suggested.

After it is completely dry, TIC 8020 Vapour Barrier Sealant may be top coated with good quality water base paint

Clean-up

Use fresh water to clean brushes and equipment before product dries. Dry product may be removed with hot soapy water or strong solvent such as chlorinated solvent (non-flammable) or xylene (flammable).

Note

Important: We make no other warranties and expressly disclaim any warranties of merchantability or fitness for a particular purpose. If a product fails to meet this limited warranty, purchaser's sole and exclusive remedy is replacement of the product or, at our option, refund of the purchase price. Our acceptance of any orders for the product is expressly conditional upon purchaser's assent to the terms on the applicable invoice.

Adequate Tests: The information contained herein we believe is correct to the best of our knowledge and tests. The recommendations and suggestions herein are made without guarantee or representation as to results. We recommend that adequate tests be performed by you to determine if this product meets all of your requirements. The warranted shelf life of our products is six months from date of shipment to the original purchaser.

TIC CORPORATION

Headquarter & Factory: 106, 5sandan-2ro, Seongnam-myeon, Dongnam-gu, Cheonan-si, Chungcheongnam-do Province, Republic of Korea Tel +82 41 558 4252(Rep), Fax +82 41 558 9360, e-mail tic@tickorea.com
www.tickorea.com